

VONTRON SW8040LE-400 RO Element


Brief Introduction

SW series of sea water aromatic polyamide RO element developed by VONTRON for seawater desalination. This series of elements have the characteristics of low operating pressure, low equipment investment, good desalination performance and stability. Among them, the SW8040XHR-400 have the highest desalination rate of 99.85%, which ensure that drinking water can be produced from seawater through one pass RO system.

SW series membrane elements are generally suitable for the treatment of seawater and brackish water with high concentration. It can be used for seawater desalination, desalination of brackish water with high concentration, boiler replenishment water in power plants, wastewater reuse, concentration and recovery of high value-added substances such as food and pharmaceuticals, etc.

Model	Active Membrane Area ft ² (m ²)	Average Permeate GPD(m ³ /d)	Stable Rejection Rate %	Spacer Thickness mil
SW8040LE-400	400 (37.2)	9000 (34.0)	99.8	34
Testing Conditions	Testing Pressure		800 psi (5.52Mpa)	
	Testing Solution Temperature		25 °C	
	Concentration of Testing Solution (NaCl)		32000ppm	
	pH value of Testing Solution		8%	
	Recovery Rate of Single Element		8 %	
Operating	Max. Working Pressure		1200psi (8.28Mpa)	
	Max. Volume of Feed water		75gpm (17 m ³ /h)	
	Max. Temperature of Feed water		45°C	
	Max. Feed water SDI ₁₅		5	
Limit & Conditions	pH Range of Feed water during Continuous Operation		2~11	
	pH Range of Feed Water during Chemical Cleaning		1~13	
	Residual Chlorine Concentration of Feed Water		<0.1ppm	
	Max. Pressure Drop of Single Membrane Element		15psi (0.1Mpa)	

Size of Membrane Element: 1.0 inch=25.4 mm



Notice:

1. All data and information provided in this manual have been obtained from long-term experiment by Vontron. We confirm the effective and accuracy of the data. Vontron assumes no liability for any aftermath caused by user's failure in abiding by the conditions specified in this manual in use or maintenance of membrane products. It is strongly recommended that the user shall strictly abide the designed use and maintenance requirements and keep relevant records.
2. The permeate value listed in the table is the average value. The permeate flow of single membrane element is tolerance not exceeding $\pm 20\%$ of the nominal value.
3. All wet-type membrane elements have been strictly tested before leaving the factory, and have been treated with 1.0% sodium hydrogen sulfite (10% glycerin antifreeze required in winter) for storage purpose, then sealed with plastic bag in vacuum, and further packed in carton boxes.
4. The membrane used should remain wet after being used; In long term suspension, to prevent the breeding of microbes, soak the membrane elements with protective solution is highly recommended, the solution (prepared with RO filtered water) containing 1.0% sodium hydrogen sulfite (foodstuff-purpose).
5. Operate low pressure flushing for 15-25 minutes of first use, high pressure flushing for 60-90 minutes when first use (Permeate volume no less than 50% of designed volume). Discard all the permeate and condensed water produced during the first one hour after system start-up.
6. During storage time and operation period, it is strictly prohibited to added any chemical medicament that may be harmful to membrane elements. In case of any violation in adding chemical medicament, Vontron assumes no liability for any damages incurred.
7. Along with technical development and product renovation, all information will be subject to modification without prior notification. Please keep notice the website of Vontron for any updates of the product.